



564 SAND FINE

## DPR SB Acrylic Finishes

Test	Method	Criteria	Results
Abrasion Resistance*	ASTM D968	No cracking or loss of film integrity at 528 quarts (500 L) of sand	Pass @ 1000 Liters
Accelerated Weathering	ASTM G153 (Formerly ASTM G 23)	No deleterious effects at 2000 hours when viewed under 5x magnification	Pass
Flexibility (Mandrel Bend)	ASTM D522, Method B	No Requirement	1" diameter @ -4°F
Freeze/Thaw Resistance*	ASTM E 2485	No deleterious effects at 10 cycles when viewed under 5x magnification	Pass @ 60 cycles
Mildew Resistance*	ASTM D 3273	No growth supported during 28 day exposure period	Pass @ 35 days
Mildew Resistance*	MIL 810 B 508		No growth 28 days
Moisture Resistance*	ASTM D2247	No deleterious effects at 14 day exposure	Pass 28 days
Salt Fog Resistance*	ASTM B117	No deleterious effects at 300 hours	Pass @ 900 hrs
Scrub Resistance	ASTM D2486	No Requirement	Pass 10,000 Cycles
Surface Burning Characteristics	ASTM E84	Individual components shall each have a flame spread <25, and smoke developed < 450	Flame Spread: 0 to 15 Smoke Developed: 0 to 15
Water Vapor Transmission	ASTM E 96 Procedure B	Vapor Permeable	Permeable
VOC	EPA Reference Test Method 24	US EPA, South Coast AQMD and Greenseal Standard	10 g/L

\*Tested with Parex Base Coat

### DESCRIPTION:

- 100% Acrylic-based textured finish
- DPR (Dirt Pick-up Resistance) chemistry
- Integrally colored with high-quality pigments
- Exceeds ASTM and ICC Acceptance Criteria

### USES:

- Exterior or interior finish coat over:
  - Parex EIFS
  - Properly prepared masonry, stucco, and concrete surfaces
  - Interior application over drywall, plaster, or properly prepared masonry or concrete

### COMPOSITION:

- Binder base: 100% acrylic polymer with surface-hardening property.
- Aggregate: Blend of natural aggregates.
- Water-based: VOC-compliant
- Pigment base: Titanium dioxide.
- Color: Parex USA standard colors or tinted to desired custom color. Meets SCAQMD Rule 1113 when using Parex USA Non-VOC Colorants

*Note: "The Plus" Advantage can be added to any Parex finish or coating. "The Plus" provides additional protection against mildew and algae growth.*

### CONTAINER:

- 65 lb (29.5 kg) net weight in plastic pails.
- Storage: Protect from direct sunlight and freezing at all times.
- Do not stack pails more than 3 pails high.
- Shelf life: Reference Parex USA Expiration Date of Products Technical Bulletin

FEATURES	BENEFITS
DPR Chemistry	High Resistance to accumulation of dirt, mold and pollutants
Integrally Colored	Reduces surface maintenance and re-coating
Low VOC	Exceeds ASTM and ICC criteria

**COVERAGE:**

Depending on the condition of the substrate and method of application, approximate coverages per pail are:

**564 Parex Sand Fine**

Aggregate size: 1.0mm  
150–165 ft<sup>2</sup> (14–15 m<sup>2</sup>)

**DRYING TIME:**

24-48 hours under normal conditions. High humidity and low temperatures extend drying time.

**CLEAN-UP:**

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

**SURFACE PREPARATION:**

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- Portland Cement Plaster must be clean and cured a minimum of 7 days or in accordance with Parex Armourwall Specifications.
- New concrete, stucco and masonry must be clean and cured a minimum of 28 days.
- Check concrete surfaces for alkalinity and treat. Any form-release agents or bond breakers must be removed.
- Uneven concrete or masonry can be leveled with a Parex 121 Base Coat & Adhesive or other suitable, compatible product.
- For interior drywall, prepare as for painting.
- Parex USA recommends the use of primers to enhance the appearance and uniformity of the finish, improved coverage, and decrease the chance of efflorescence. This is especially true when using dark colors or finishes with a large aggregate. If specified, prime with Parex USA Primer or Variance VariPrime Sanded, refer to Product Data Sheet.
- For additional options, contact Parex USA Technical Services Department.

**MIXING:**

- Use clean equipment for mixing and preparation.
- Stir to obtain a homogeneous consistency using a heavy-duty 1/2-in. (13mm) drill with a rust free paddle at 400–500 rpm. Avoid air entrainment.
- Add the amount of water needed to achieve finish texture. To avoid color variations, add the same amount of water to each pail of finish as up to 16 oz (0.5 L).

**APPLICATION:**

- Read the entire label before using this product
- Always maintain a wet edge and work to corners or joints. For best color consistency, use finish with the same batch number within a wall section. For more information, see Technical Bulletin: "Boxing Acrylic Finishes".
- Keep container closed when not in use.
- Use a clean stainless steel trowel and apply a uniform coat the thickness of the largest aggregate size of the finish.
- **564 Sand Fine:** Use a clean plastic float or stainless steel trowel. A plastic float will roll the large aggregates more than a stainless steel trowel, and may cause swirling. Continuously dry clean the plastic float or steel trowel while texturing. Use consistent pressure and motion to achieve the desired texture.
- Spray application: To achieve consistent texture, spray application must use consistent motion, pressure, distance and spray angle. A job-site mock up for spray application is advised.

*Note: This product contains natural raw materials that contain by-products that can cause discoloration; this is not a manufacturing defect.*

**LIMITATIONS:**

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, unpainted, and free from any residue that might affect the ability of the finish to bond to the surface.
- Application in direct sunlight in hot weather may adversely affect aesthetics.
- Parex USA is not responsible for color correctness after finish has been applied.

**WARNING:**

- Read complete Warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Safety Data Sheet (SDS). The most current SDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, Parex USA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Parex USA, Inc.  
4125 E. La Palma Ave., Suite 250  
Anaheim, CA 92807  
(866) 516-0061 Tech Support: (800) 226-2424



EIMA

S M A  
Stone Manufacturers AssociationPAREXUSA  
SUSTAINABILITY