



Parex Armourwall 100 Stucco is a 1-coat system providing a durable exterior stucco façade with unique, refined aesthetic appeal. This minimum 3/8" thick system can be installed at greater thicknesses in accordance with ASTM C926 as required for fire resistance rated assemblies or STC ratings. Enhanced Krak-Shield crack-resistance is available for all configurations by incorporating a reinforced leveling coat prior to application of the finish.

Suitable Types of Construction

Non-combustible
Combustible
Fire-Resistance Rated Walls
Application Type
Application Orientation

Residential
 Residential
 Residential
 New
 Exterior Only

Commercial
 Commercial
 Commercial
 Renovation

Substrates

Gypsum Sheathing
Fiber Board
Exposure 1 OSB¹

Cement Fiber Sheathing
Concrete & CMU
CDX Plywood²

¹Regional restrictions apply. For OSB applications outside of approved regions, use Parex Standard WaterMaster LCR.
²See Tech Bulletin TB008 and TB011.

Code Approvals

ICC ESR-2564
State of Florida FL 12427

System Notes

- Stucco is a non-structural cladding. It depends on the substrate wall for support and attachment. Substrate construction must resist all design loads.
- Sheathing attachment to framing must resist design negative windloads; loads are transferred to the framing. Appropriate safety factors must be applied.
- All penetrations & non-draining terminations of the system must be made weather-tight.
- Armourwall 100 stucco systems can be installed with lath or direct applied over CMU. When direct applied over CMU, Parex WeatherDry is installed over the brown coat prior to application of the finish. See Parex USA Tech Bulletin TB029.

Components

System options vary based on assembly selected. Review Parex Stucco Systems for more detailed system information.

➤ **WRB, Field Substrate**

-A code compliant water-resistive barrier

Used with Standard stucco assemblies.

➤ **Lath & Accessories**

- Minimum G60 Galvanized Steel

- OR -

-Rigid Polyvinyl Chloride (PVC)

- OR -

-Zinc Alloy

- Lath Locks: Wind-lock galvanized steel washer, 1 ¼" d, 24 gauge

- Metal Plaster Base: Minimum 17 gauge, self-furred, 2.5 lb/yd²

- Foundation Weep Screed, minimum 3 ½" vertical attachment flange

Note: Select appropriate lath & accessories for the building type.

➤ **Base/Brown Coat**

- Parex 210 or 202 Armourwall Stucco Base

Sanded and Concentrate formulations are available.

➤ **Stucco Admix (use with Scratch & Brown Coat materials)**

- Parex USA Adacryl Admix & Bonding Agent (optional)

For enhanced adhesion, curing, freeze-thaw stability & workability.

➤ **Krak-Shield, Enhanced Crack Resistance (Optional)**

- A Parex 121 Basecoat & Adhesive*

or Parex USA Stucco Level Coat

- Reinforcing Mesh: 4.5 oz or 12 oz for stucco applications

** Select the formulation most suitable for the project*

➤ **Primer (Optional, use with acrylic & elastomeric finish materials)**

- A Parex USA primer suitable for finish selected

The use of primer enhances appearance and uniformity of the finish, improves finish coverage rates, helps prevent efflorescence, and promotes adhesion.

➤ **Finish or Coating**

- A Parex acrylic, elastomeric or specialty finish

NOTE: EPS Features & Shapes can be added as desired.

➤ **Sealers & Accent Stains (Optional)**

- A Parex USA sealer or accent stain to enhance aesthetics & cleanability.

Primarily used with specialty finishes

PAREX®

Corporate Office

Parex USA, Inc., a California Corporation
4125 E. La Palma Ave., Suite 250

Anaheim, CA 92807

www.parex.com

866-516-0061

Tech Support: 800-226-2424

© Parex USA, Inc. November 2017 • SSS AW100 1117